

electrically connected to the side surface electrode disposed on the side surface of the piezoelectric device.--

**IN THE CLAIMS:**

Please cancel non-elected claims 9-30 without prejudice or disclaimer.

Please amend the claims as follows.

1. (Amended) A piezoelectric device for an injector, built into an injector and generating driving force of said injector, comprising:

a plurality of piezoelectric layers generating displacement in proportion to a voltage applied to said piezoelectric layers;

a plurality of internal electrode layers for supplying the applied voltage;  
and

said piezoelectric layers and said internal electrode layers being alternately laminated;

the composition of said piezoelectric layers being a lead zirco-titanate composition, the components of said lead zirco-titanate composition being adjusted so that a relation  $d(0.1 E_c)/d(1.2 E_c) > 0.43$  is established, where  $E_c$  is coercive electric field which causes the changing of polarizing direction, between an apparent piezoelectric constant  $d(1.2 E_c)$  calculated from static elongation when an electric field of  $1.2 E_c$  is applied to said piezoelectric device in the same direction as a polarizing direction while a preset load of 500N is applied to said piezoelectric device, and an apparent piezoelectric constant  $d(0.1 E_c)$  calculated from static elongation when an electric field of

0.1 Ec is applied to said piezoelectric device in the same direction as the polarizing direction.

2. (Amended) A piezoelectric device for an injector according to claim 1, wherein the components of the lead zirco-titanate composition establish a relation  $d(0.1E_c)/d(1.2E_c) \geq 0.5$  between said piezoelectric constant  $d(1.2E_c)$  and said piezoelectric constant  $d(0.1E_c)$ .

3. (Amended) A piezoelectric device for an injector, built into an injector and generating driving force of said injector, comprising:

a plurality of piezoelectric layers generating displacement in proportion to a voltage applied to said piezoelectric layers;

a plurality of internal electrode layers for supplying the applied voltage;  
and

said piezoelectric layers and said internal electrode layers being alternately laminated;

the composition of said piezoelectric layers being a lead zirco-titanate composition, the components of said lead zirco-titanate composition being adjusted so that said piezoelectric device has a change ratio of displacement of 9% or below when a frequency of the applied voltage is changed from 1 Hz to 200 Hz under the state where an AC voltage is applied so that an electric field intensity of 0 to 1.5 kV/mm is generated by a sine wave while a preset load of 500N is applied to said piezoelectric device.

4. (Amended) A piezoelectric device for an injector according to claim 3, wherein said change ratio of displacement is 7% or below.

5. (Amended) A piezoelectric device for an injector, built in an injector and generating driving force of said injector, comprising:

a plurality of piezoelectric layers generating displacement in proportion to a voltage applied to said piezoelectric layers;

a plurality of internal electrode layers for supplying the applied voltage;  
and

said piezoelectric layers and said internal electrode layers being alternately laminated;

the composition of said piezoelectric layers being a lead zirco-titanate composition, the components of said lead zirco-titanate composition being adjusted so that the displacement increases with the rise of temperature within the range of -40°C to 150°C.

6. (Amended) A piezoelectric device for an injector according to claim 5, wherein the components of the lead zirco-titanate composition is adjusted so that said change ratio of displacement is 5 to 40% within the range of temperature of -40°C to 150°C.

7. (Amended) A piezoelectric device for an injector, built in an injector and generating driving force of said injector, comprising:

a plurality of piezoelectric layers generating displacement in proportion to a voltage applied to said piezoelectric layers;

a plurality of internal electrode layers for supplying the applied voltage;

and

said piezoelectric layers and said internal electrode layers being alternately laminated;

the composition of said piezoelectric layers being a lead zirco-titanate composition, the components of said lead zirco-titanate composition being adjusted so that said piezoelectric device has a dielectric loss of 8% or below calculated from a P-E hysteresis.

8. (Amended) A piezoelectric device for an injector according to claim 7, wherein the components of said lead zirco-titanate composition being adjusted such that said dielectric loss is 7% or below.

Please add the following new claims.

--31. (New) A method of using a piezoelectric device to generate a driving force of an injector, the piezoelectric device having a plurality of piezoelectric layers and a plurality of internal electrode layers, the method comprising:

applying a voltage to the plurality of internal electrode layers;

generating displacement in the piezoelectric layers in proportion to the applied voltage; and

establishing a relation  $d(0.1E_c)/d(1.2E_c) > 0.43$ , where  $E_c$  is coercive electric field which causes the changing of polarizing direction, between an apparent piezoelectric constant  $d(1.2E_c)$  calculated from static elongation when an electric field of  $1.2 E_c$  is applied to said piezoelectric device in the same direction as a polarizing direction while a preset load of 500 N is applied to said piezoelectric device, and an apparent piezoelectric constant  $d(0.1E_c)$  calculated from static elongation when an electric field of  $0.1 E_c$  is applied to said piezoelectric device in the same direction as the polarizing direction.

32. (New) A method according to claim 31, wherein a relation  $d(0.1E_c)/d(1.2E_c) \geq 0.5$  is established between said piezoelectric constant  $d(1.2E_c)$  and said piezoelectric constant  $d(0.1E_c)$ .

33. (New) A method of using a piezoelectric device to generate a driving force of an injector, the piezoelectric device having a plurality of piezoelectric layers and a plurality of internal electrode layers, the method comprising:

applying a voltage to the plurality of internal electrode layers;

generating displacement in the piezoelectric layers in proportion to the applied voltage; and

wherein said piezoelectric device has a change ratio of displacement of 9% or below when a frequency of the applied voltage is changed from 1 Hz to 200 Hz under the state where an AC voltage is applied so that an electric field intensity of 0 to 1.5 kV/mm is generated by a sine wave while a preset load of 500 N is applied to said piezoelectric device.

34. (New) A method according to claim 33, wherein said change ratio of displacement is 7% or below.

35. (New) A method of using a piezoelectric device to generate a driving force of an injector, the piezoelectric device having a plurality of piezoelectric layers and a plurality of internal electrode layers, the method comprising:

applying a voltage to the plurality of internal electrode layers; and  
generating displacement in the piezoelectric layers in proportion to the applied voltage;

wherein the displacement increases with the rise of temperature within the range of -40°C to 150°C.

36. (New) A method according to claim 35, wherein said change ratio of displacement is 5 to 40% within the range of temperature of -40°C to 150°C.

37. (New) A method of using a piezoelectric device to generate a driving force of an injector, the piezoelectric device having a plurality of piezoelectric layers and a plurality of internal electrode layers, the method comprising:

applying a voltage to the plurality of internal electrode layers; and  
generating displacement in the piezoelectric layers in proportion to the applied voltage;

wherein said piezoelectric device has a dielectric loss of 8% or below calculated from a P-E hysteresis.

38. (New) A method according to claim 37, wherein the dielectric loss is 7% or below.--

### **REMARKS**

Reconsideration and allowance of this application are respectfully requested. Currently, claims 1-8 and 31-38 are pending in this application.

Attached hereto is a marked-up version of the changes made to the specification and claims by the current Amendment. The attached is captioned **“Version With Markings to Show Changes Made.”**

### **Rejection Under 35 U.S.C. §103:**

Claims 1-8 were rejected under 35 U.S.C. §103 as allegedly being unpatentable over Igashira et al (U.S. ‘074, hereinafter “Igashira”). Applicant respectfully traverses this rejection.